



3145 County Hwy G, Rhinelander, WI 54501  
Ph. 715-369-5700, [www.enterprisewood.com](http://www.enterprisewood.com)

## Reclaimed Timber

**Species:** Varies depending on current availability. Select species typically not offered.

**Surfacing:** Original Face will be available in nominal dimension and S4S (Surfaced 4 Sides) will be available in actual/dimensional widths always less than the nominal dimension.

**Dimension:** Original Face 4x4 through 12x12. Surfaced available depending on the maximum dimension allowed by the material (may vary depending on current material)

**Due to Original Face reclaimed timbers being left natural there may be variability in dimension from timber to timber.**

**\*PLEASE NOTE THAT S4S SURFACED TIMBERS WILL HAVE SHARPER EDGES AND AN EASED EDGE (1/8") SHOULD BE REQUESTED IF THIS IS NOT DESIRED\***

**Lengths:** Random lengths

- Specific Lengths available upon request for an additional charge pending availability.

**Texturing Options:** Original Face, S4S (Surfaced 4 Sides)

**Grades:** Rustic

- Rustic Reclaimed timbers may contain large amounts of character including mortise and tenon cuts, notches/holes that may penetrate the entirety of timber, nail holes, blown out knots, and circle/band sawn/hatchet hewn kerf character.

**Finish Options:** Unfinished, Oil Based Polyurethane or Lacquer, Water Based Polyurethane or Lacquer

- Staining available for an additional charge. Staining rough sawn material will lead to a drastically darker product than the same stain color on surfaced material. It is also recommended to request pre-stain conditioner on softwoods to avoid blotchiness.
- Pre-finished reclaimed material will always be patina sanded unless otherwise requested. If a customer chooses not to sand the product the finish will be slightly rougher to the touch.

**Acclimation:** Recommended acclimation period of 2 weeks of proper storage at the job site.

- Keep proper humidity levels in your home or business between 35% to 55%
- It is recommended to measure humidity levels in your home using a hygrometer
- Timbers may contain cracks/checks in the surface that penetrate towards the center/heart of the tree. These are considered character and not a defect unless the crack proceeds through the entire timber and compromises the integrity of the piece. EWP will use it's judgement on a crack/check that proceeds further than the center/heart of the tree.

#### **Reaction to Environmental Conditions**

- Wood is a product of nature and will act naturally. It will expand and contract as it gains and loses moisture. Timbers will crack/check during low-humidity seasons and this is not considered a defect. Maintaining optimum humidity levels of 30 to 55% will minimize these occurrences. Allowing relative humidity levels to fall below 30% can result in dramatic large gaps, splits in the surface, distortion of the boards and possible structural failure/integrity of the timber. Humidity levels above 55% can result in surface warping/swelling and may compromise structural integrity.

#### **Light Exposure:**

- Varying changes (patina) can occur when wood is exposed to UV rays from sunlight, florescent, LED, and incandescent bulbs. Window coverings, UV resistant tint, solar screens can minimize but not eliminate this natural occurrence. Certain species are more susceptible to light & development of varying degrees/shades of patina, due to their high content of natural oils.

**Maintenance:** Pine is a softer wood and is more susceptible to scratches and dents.

- Clean with a product recommended for use on wood surfaces.